



ISOLAC-DUCO SATIN

Satin, hard-wearing enamel paint for metal

Description

ISOLAC-DUCO SATIN is a premium enamel paint for metal surfaces. It features high hardness and surface coverage while providing excellent resistance to weather conditions and aging. It dries fast to a satin, highly wear- and impact-resistant final surface. Suitable for interior and exterior use

Fields of application

ISOLAC-DUCO SATIN is used for indoor or outdoor applications, on new or old metal surfaces, such as doors, railings, machinery, and tools.

Technical data

Colors: white, black and a wide

range of colors though ISOMAT COLOR SYSTEM

Type: alkyd-based enamel paint

Volume solids: 45 ± 2%

Density (White): $1.20 \pm 0.03 \text{ kg/l}$

(EN ISO 2811-11)

Viscosity

Brookfield (23°C): 800-1,200 mPa·s

(EN ISO 2884-2)

Adhesion: $\geq 2.0 \text{ N/mm}^2$

(EN ISO 4624)

Dry film thickness: $45 \pm 5 \mu m$

(WFT: 100 µm) (EN ISO 2808)

Drying time: 40 min (touch dry) 6 h (through dry)

Recoat time: 24 h

(EN ISO 9117)

Water vapor

permeability: $S_d = 10.50 \pm 0.50 \text{ m}$ (EN ISO 7783- 2: $V_3 \text{ low}$, $S_d \ge 1.4 \text{ m}$)

Capillary water

absorption: $w = 0.01 \pm 0.005 \text{ Kg/m}^2 h^{0.5}$

(EN ISO 1062-3: W_3 low, w < 0.1) Fineness of grind: $\leq 10 \mu m$ Measurements acc. to EN 13300

Gloss level: 25-55, Satin

(EN ISO 2813: < 60 at 60°)

Opacity: \geq 98% (2 coats of 100 µm wet)

(EN ISO 6504-3)

Whiteness: ≥ 82%

(EN ISO 6504-3)

Wet scrub resistance: CLASS 1 (EN ISO 11998: 0.8 < 5 μm at 200 washing cycles)

Cleaning of tools:

Remove as much paint as possible from the used tools before cleaning. Clean tools thoroughly with SM-21 or SM-22 immediately after use.

Directions for use

1. Substrate preparation

The substrate should be dry and free of dust, oil, grease, loose particles, etc., while any imperfections should be smoothed down with sandpaper. The surface is then primed with ISOLAC-RUST PRIMER.

For application to galvanized metal or aluminum surfaces, priming with EPOXYCOAT-AC is necessary to achieve maximum adhesion.

After 24 hours, provided the primer has completely dried, the first coat of ISOLAC-DUCO SATIN can be applied.

2. Application

Stir ISOLAC-DUCO SATIN well before use. For brush or roller application, thin up to 5% with SM-21 and for airless spray application thin 10-20% with SM-22. Apply two coats allowing the first coat to dry completely before applying the second, after approximately 24 hours.

Temperature during application and drying of the paint should be between +10°C and +35°C.

Coverage

ISOLAC-DUCO SATIN covers approx. 15 m²/l per coat, on previously prepared surfaces.







ISOLAC-DUGO SATIN

Packaging

ISOLAC-DUCO SATIN is available in 0.75 I and 2.5 I containers.

Shelf life - Storage

24 months from production date if stored in original, unopened packaging at temperatures between +5°C and +35°C. Protect from direct sunlight and frost.

Volatile Organic Compounds (VOCs)

According to Directive 2004/42/EC (Annex II, table A), the maximum allowed VOC content for the product subcategory i, type SB, is 500 g/l (2010) for the ready-to-use product.

The ready-to-use product ISOLAC-DUCO SATIN contains a maximum of 500 g/l VOC.



2032

ISOMAT S.A.

17th km Thessaloniki – Ag. Athanasios P.O. BOX 1043, 570 03 Ag Athanasios, Greece

18

2032-CPR-10.11

DoP No.: ISOLAC DUCO / 1439-01

EN 1504-2

Surface protection products

Coating

Permeability to CO₂: Sd > 50m

Water vapor permeability: Class I (permeable)

Capillary absorption: w < 0.1 kg/m²·h^{0.5}

Adhesion: ≥ 0.8 N/mm²

Reaction to fire: Euroclass F

Dangerous substances comply with 5.3

ISOMAT S.A.
BUILDING CHEMICALS AND MORTARS
MAIN OFFICES - FACTORY:

17th km Thessaloniki - Ag. Athanasios Road, P.O. BOX 1043, 570 03 Ag. Athanasios, Greece, Tel.: +30 2310 576 000, Fax: +30 2310 576 029

www.isomat.eu e-mail: support@isomat.eu