

ISOLUX

Colored wood varnish

Description

Premium quality varnish for wooden surfaces. Suitable for both interior and exterior use. ISOLUX is characterized by high elasticity, water repellency and breathability. It has UV filters and shows excellent resistance to weather conditions and aging. It shows high adhesion, is easy to work with and dries fast. It is available in satin, colored in 8 selected colors or transparent which may be colored in more hues.

Fields of application

ISOLUX is used in indoor or outdoor applications, on old or new wooden surfaces (e.g. doors, windows, wooden constructions, garden furniture, etc.), in order to protect and bring out the natural beauty of wood.

Technical data

Colors:
2,5 lt containers: transparent & 5 colors
0,75 lt containers: transparent & 8 colors

Type: enamel paint

Classification by gloss (EN 13300):
Satin= 59
(EN ISO 2813: < 60, angle of incidence 60°)

Density: 0.92 ± 0.02 kg/l
(EN ISO 2811- 1)

Viscosity(mPa.s): 560 (23 °C)
(EN ISO 2884- 2)

Capillary water absorption: 0.02 kg/m²/h^{0.5}
(EN ISO 1062- 3: W₃Low, w ≤ 0,1)

Adhesion: 2 N/mm²
(EN ISO 4624)

Drying time: 7 h (touch dry)
(EN ISO 9117)

Recoating in: 24 h
(EN ISO 9117)

Cleaning of tools:

Remove as much material as possible from the tools before cleaning them. Clean the tools with SM-18 or white spirit, immediately after use.

Directions for use

1. Substrate preparation

The substrate should be dry and free of grease, dust, etc., while any imperfections should be rubbed down with sandpaper. Before the application of ISOLUX, it is recommended to apply two coats of ISOXYL, the special, transparent preservative for the protection of wood from woodworm and fungi.

2. Application

Before using ISOLUX, stir well. Apply with a brush or roller in two layers, as it is or thinned up to 3% with SM-18. The second layer is applied as soon as the first one has completely dried. Temperature during application and drying of the varnish should be between +10°C and +35°C.

Coverage

ISOLUX covers 12-18 m²/l, depending on the hardness of the wood.

Packaging

ISOLUX: available in 0.75 l and 2.5 l containers.

Shelf-life / Storage

24 months from production date, if stored in original, unopened packaging, at temperatures between +5°C and +35°C. Protect from direct sun exposure and frost.

Volatile Organic Compounds (VOCs)

The maximum allowed VOC content for the product subcategory A/f (interior and exterior minimal build woodstains), is 700 g/l (2010) for the ready-to-use product.

The ready-to-use product ISOLUX contains a maximum of 600 g/l VOC.

ISOMAT S.A.

BUILDING CHEMICALS AND MORTARS

Thessaloniki: 17th km Thessaloniki - Ag. Athanasios Road,
P.O. BOX 1043, 570 03 Ag. Athanasios, Greece,

Tel.: +30 2310 576 000, Fax: +30 2310 722 475

Athens: 57th km Athens-Lamia N.R., 32011 Inofita, Greece

Tel.: +30 22620 56406 Fax: +30 22620 31644

www.isomat.eu e-mail: info@isomat.eu

The technical information and instructions supplied in this datasheet are based on the knowledge and experience of the Department of Research and Development of our company and on results from long-term applications of the product in practice. The recommendations and suggestions referring to the use of the product are provided without guarantee, since site conditions during the applications are beyond the control of our company. Therefore the user is responsible for confirming that the chosen product is suitable for the envisaged application. The present edition of this technical datasheet automatically cancels any previous one concerning the same product.

